



ARDE Part Number 4307			
Volume (cubic inches)	3157	Material of Construction	
Operating Pressure (psig)	4500	Liner	Cryoformed CRES 301
Proof Factor	1.25	Porting Interface	CRES 304L
Minimum Burst Factor	1.5	Wrap	IM7-W
Actual Rupture Pressure (psig)	7350		HARF 53
Weight (pounds)	23.5		Liner/Composite Bond-None
Qualification Basis Standard	MIL-STD 1522A	Environmental Load (He)	Component Qual
	AIAA-S081		Axial 22.2 g _{rms}
			Lateral 22.2 g _{rms}