



ARDE Part Number 4664			
Volume (cubic inches)	5920	Material of Construction	
Operating Pressure (psig)	4550	Liner	Inc 718
Proof Factor	1.25	Porting Interfaces	CRES 21-6-9 Tube/Mechanical Port
Minimum Burst Factor	1.5	Wrap	Fiber: T-1000
Actual Rupture Pressure (psig)	8844 @200F 9200@RT		Resin: ARDE 31-43B
Weight (pounds)	41.5		Adhesive-Cytec FM-73
Qualification Basis Standard	MIL-STD 1522A	Environmental Load	Contact ARDE
	AIAA-S081		