



ARDE Part Number 4698			
Volume (cubic inches)	548	Material of Construction	
Operating Pressure (psig)	5800	Liner	Al-2219
Proof Factor	1.25	Porting Interface	304L Tube
Minimum Burst Factor	1.5	Wrap	Fiber: T-1000
Actual Rupture Pressure (psig)	14758		Resin: ARDE 31-43B
Weight (pounds)	6.9		Adhesive-Cytec FM-73
Qualification Basis Standard	MIL-STD 1522A	Environmental Load (N ₂)	Component Qual
	AIAA-S081		Axial 26.2 grms