



ARDE Part Number 5016			
Volume (cubic inches)	8100	Material of Construction	
Operating Pressure (psig)	5000	Liner	I-718
Proof Factor	1.25	Tubing Interface	CRES 625
Minimum Burst Factor	1.5	Wrap	Fiber: T-800
Actual Rupture Pressure (psig)	9260		Resin: ARDE 31-43B
Weight (pounds)	70		Liner/Composite Bond-None
Qualification Basis Standard	MIL-STD 1522A		
	AIAA-S081		