



ARDE Part Number 5055			
Volume (cubic inches)	1678	Material of Construction	
Operating Pressure (psig)	4133	Liner	Cryofomed CRES 301
Proof Factor	Porting	Tubing Interface	CRES 304L
Minimum Burst Factor	1.5	Wrap	Fiber: T-1000
Actual Rupture Pressure (psig)	12,500 by Similarity		Resin: ARDE 31-43B
Weight (pounds)	17.0	Environmental Load	Liner/Composite bond-none
Qualification Basis Standard	MIL-STD 1522A		Contact ARDE
	AIAA-S-081		